

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C12P 7/62, C08G 63/06	A1	(11) International Publication Number: WO 96/09402 (43) International Publication Date: 28 March 1996 (28.03.96)
(21) International Application Number: PCT/GB95/02257 (22) International Filing Date: 21 September 1995 (21.09.95) (30) Priority Data: 9419082.4 22 September 1994 (22.09.94) GB (71) Applicant (for all designated States except US): ZENECA LIMITED [GB/GB]; 15 Stanhope Gate, London W1Y 6LN (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): COX, Michael, Kenneth [GB/GB]; Hanami, Bedlam Hill, Borrowby, Thirsk, North Yorkshire YO7 4QQ (GB). HAMMOND, Timothy [GB/GB]; 12 Craggside, Sedgefield, Stockton on Tees, Cleveland TS21 2DQ (GB). WOOD, John, Christopher [GB/GB]; 58 Berwick Chase, Oakerside Park, Peterlee, Co Durham SR8 1NQ (GB). (74) Agents: LOCKE, Timothy, John; Intellectual Property Group, Zeneca Bioproducts, P.O. Box 2, Belasis Avenue, Billingham, Cleveland TS23 1YN (GB) et al.		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: COPOLYESTERS (57) Abstract A hydroxycarboxylic acid copolyester of R-stereospecific configuration contains a majority of first repeating units capable of forming a highly crystalline high-melting homopolyester and a minority of second repeating units capable when randomly copolycondensed with said first repeating units of lowering the melting point of said homopolyester and is characterised by one or more of: higher crystalline melting point, shorter crystallising time, higher notched impact strength at age 1 month, as compared with corresponding random polyester, and said majority repeating units in the polyester chain being present in blocks longer than correspond to their over-all molar proportionality. The copolyester may be made by fermentation, controlling the distribution of repeating units by reference to the pattern of feeding substrates corresponding to the respective repeating units.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

COPOLYESTERS

THIS INVENTION relates to copolyesters and in particular to those having hydroxy acid repeating units.

Polycondensed hydroxyacids, especially those of R-
5 stereospecific configuration made microbiologically, have recently become commercially available. Of these, poly-3-hydroxybutyric acid homopolymer (PHB) is capable of a high level of crystallinity, but melts at the relatively high temperature 174-180°C, at which loss of molecular
10 weight is relatively rapid. Copolymers (PHBV) containing 3-hydroxyvalerate units at eg 3-30 mol percent melt at a lower temperature and are correspondingly more stable during melt-processing, but they crystallise more slowly.

We have now found that the crystallisation behaviour
15 can be influenced favourably by bringing the repeating units together in a special configuration.

ACCORDING TO THE INVENTION a hydroxycarboxylic acid copolyester of R-stereospecific configuration contains a majority of first repeating units capable of forming a
20 highly crystalline high-melting homopolyester and a minority of second repeating units capable when randomly copolycondensed with said first repeating units of lowering the melting point of said homopolyester:
characterised by one or more of the following features:

- 25 a a crystalline melting point higher by at least 10, especially by at least 15, °C than that of the corresponding random copolyester;
- b a half-crystallising time at 70°C or 120°C less than 0.9, especially less than 0.5, of that of the
30 corresponding random copolyester;
- c IZOD 1mm notched impact strength at age 1 month at least equal to that of the corresponding random

polyester of 20% higher molecular weight;

d said majority repeating units in the polyester chain present in blocks longer than correspond to their over-all molar proportionality.

5 The repeating units in the copolyesters preferably include the residues of 3-hydroxybutyric acid (HB) and other hydroxy acids especially 4-hydroxybutyric acid (4HB) or 3-hydroxyvaleric acid (HV). Preferably HB units are in a majority, especially at least 70, especially at
10 least 80, for example 70-98 mol percent of the total units. If desired, the minority units may be of more than one chemical formula. Polyesters containing HB and HV units are referred to hereinafter as "PHBV".

The molecular weight of the polyesters is typically
15 in the range 100000 to 2000000, conveniently 150000 to 1000000. It appears that acceptable mechanical properties are obtainable at molecular weights lower than have been necessary when using random copolyesters of a similar over-all chemical composition.

20 The invention provides also processes for making the copolymers particularly by fermentation, characterised by controlling the distribution of repeating units by reference to the pattern of feeding substrates corresponding to the respective repeating units,

25 In such a process the following procedures are used: preferably fed batch operation; alternating introduction of substrates corresponding to the respective repeating units. Generally a predetermined fraction of the intended
30 consumption of each substrate is fed over a period of time and then withheld until its

concentration in the medium is about zero;
that is, has fallen to a level between 1% of
its maximum fed concentration and the level at
which the organism has begun to net-consume
5 its store of polyester. The changeover point
may be the same or different for the
respective feedstocks. The first feedstock fed
may be the majority feedstock or the minority
feedstock. The materials actually fed may be
10 chemically 100% of one feedstock or may be a
mixture of chemical compounds all producing
the same repeating unit, or may be a mixture
preponderantly producing one repeating unit
but with a small proportion - for example 0.01
15 to 1.0 % w/w producing another. The feed times
of each feedstock can be for example in the
range 0.5 to 20 h, depending on how great a
departure from randomness is required.

preferably a polyester lay-down stage in which a nutrient
20 essential for cell growth is limited; the limiting
nutrient is preferably phosphorus, rather than
nitrogen but is fed at a concentration permitting a
moderate cell growth during polyester lay-down;
preferably medium-soluble nitrogen present;
25 this also appears to provide for the moderate
cell growth.

The microorganism used in the fermentation may be
any capable of laying down a crystallisable copolyester.
When the copolyester is PHBV with PHB in the molar
30 majority, the organism is suitably a bacterium of the
genera Alcaligenes, Athiorhodium, Azotobacter, Bacillus.

Nocardia, Pseudomonas, Rhizobium or Spirillum. It may be genetically modified, or the required genetic material may have been grafted into a foreign organism such as a eukariote. Particularly preferred microorganisms are
5 selected from Alcaligenes eutrophus and Alcaligenes latus. Organisms lacking metabolic pathways to produce PHB from feedstocks of odd carbon numbers are especially preferred, since these produce purer PHV in the PHV phase of the fermentation: an example is the modified A.
10 eutrophus NCIMB 40124 described in our EP-A-0431883.

The feedstocks in making PHBV copolyesters may be for example:

for HB units: hexoses such as glucose, fructose, gluconate; alcohols and carboxylates having a linear even
15 number of carbon atoms, for example ethanol, acetate and n-butyrate;

for HV units: alcohols and carboxylates having a linear odd number of carbon atoms, for example n-propanol and propionate.

20 The copolyester can be recovered from the fermentation biomass by known methods, for example solvent extraction or by harvesting, that is, decomposition of non-copolyester cell material. Such decomposition is described in our EP-A-0145233 and more
25 recent patent applications. The polyester product can be in the form of dry solid particles or an aqueous latex. As a result of faster crystallisation, polyesters according to the invention can be harvested as dry solid more easily than corresponding random polyesters,
30 especially those rich in HV, for example over 12 mol percent.

The invention makes it possible to provide polyesters having the same raw chemical composition but a range of mechanical properties, a great increase in convenience compared with changing the feeds to the fermenter and maintaining an inventory of different polyesters for blending.

The polyesters are suitable for use in known shaping procedures and for making articles for which random PHAs are used or proposed. Since they are capable of relatively fast crystallisation they are especially suitable for melt shaping procedures such as extrusion, injection moulding and compression moulding, in which an article is formed in its final shape without mechanical treatment to increase crystallinity substantially. They may be used in processes such as fibre spinning, film extrusion and film casting, and also in such processes, including injection blow moulding with one or more steps of stretching to increase crystallinity towards the maximum attainable. Their faster crystallisation permits shorter cycle times than are at present convenient. The invention polyesters appear to undergo less secondary crystallisation after shaping than do the known random polyesters and thus are less subject to change in mechanical properties after shaping.

The polyesters can be used in solution processing, using for example chloroform, dichloromethane or 1,2-dichloroethane as solvent. If recovered from microbiological cells as latex, or converted to latex by emulsifying a solution and removing the solvent, they can be used in the generality of latex applications, especially coated or bonded products for example coated

or bonded paper or cellulose or as a paint component.

In these use operations the polyesters can be formulated, as appropriate with usual processing additives such as pigments, fillers, fibres and plasticisers.

Example 1

The following preparation was carried out three times:

An aqueous medium containing the following, expressed in g per l, and having a pH of about 7 (controlled by ammonia addition) was prepared:

MgSO ₄ .7H ₂ O	2.2
K ₂ SO ₄	3.0
Na ₂ SO ₄	0.18
FeNH ₄ citrate	0.17
Glucose	60 (corrected error)
Trace (SO ₄ : Cu 4.5mg, Zn 90mg, Mn 40mg; Ca acetate 360mg)	
Phosphoric acid	1.69 (ml of 16M).

A fermenter containing 3 litres of the above medium was inoculated with a starter culture of Alcaligenes eutrophus detailed below. The medium was incubated at 34°C for 24h until the phosphate content of the medium became limiting.

Each medium was used to produce PHBV from feedstock totalling 400g of carbon (as C) per g of phosphorus (as P) present. The organisms and feedstocks to the three batches were as follows:

A (control): NCIMB 12080 as a variant deposited under the reference NCIMB 40529; glucose (80% of total carbon) and propionic acid (20% of total carbon),

fed over 48h at rates giving near-maximal production speed;

5 B NCIMB 40124 (see our EP-A-0431883); glucose (60% of total carbon) initially 56g over 1h; then propionic acid (40% of total carbon) 19g over 1h; then this hourly cycle repeated to 62h, varying feed rates to give near-maximal production speed;

10 C NCIMB 40124; glucose and propionic acid in the same over-all carbon proportion as in B; propionic acid below toxic limit for 7h; glucose for 13h; propionic acid below toxic limit for 13h; glucose for 11h.

15 In each run the medium was agitated and air-sparged at a rate avoiding oxygen-limitation and build-up of unreacted feedstock. The resulting cells were harvested by heating, treating with protease, oxidising with hydrogen peroxide and separating polyester by centrifuging.

The dry cell weight in the batches was:

20 A: 150 g/l (70% w/w PHBV); B: 108 g/l (62% w/w PHBV);
 C: 128 g/l (62% w/w PHBV).

The polyester products were:

25 A: 88 mol percent HB, 12 mol percent HV;
 (This is a substantially random copolyester).
 B: 88 mol percent HB, 12 mol percent HV;
 (The repeating units in this copolyester are believed to be present in short blocks consisting of or preponderating in HB or HV).
 C: 88 mol percent HB, 12 mol percent HV.
 (The repeating units in this copolyester are
30 believed to be present in blocks each longer than in B).

TEST METHODS**MECHANICAL TESTS**

Polyester samples were powder blended with 1 phr of boron nitride nucleant and melt processed in a Betol single screw extruder through a 5mm circular die and granulated to chips. These were injection moulded into test bars. Tensile bars were of gauge length 40mm with typical cross-sectional areas 2.4 x 5.3mm. and were tested on an Instron 1122 instrument fitted with a NENE data analysis program. A crosshead speed of 10mm per min was used. Izod impact strength was determined using a Zwick pendulum apparatus.

THERMAL ANALYSIS: for Differential Thermal Analysis (DSC) a Mettler TA 4000 instrument was operated under programmed heating control from 20 to 200°C at 20°C per min to measure melting behaviour. Tg was measured by this sequence : heating from 20 to 200°C at 100°C per min; quenching the molten material to -45°C by cooling at 100°C per min; reheating the amorphous sample to 100°C at 20°C per min. Tg was the point of inflexion in the heating trace.

Crystallisation half times were measured by DSC : A 10 mg sample was melted by heating to 200°C at 20°C per min; held at 200°C for 2 min; rapidly cooled at 100°C per min to crystallisation temperature 70°C (non-nucleated) or 120°C (nucleated); held isothermally at that temperature for up to 1h and the crystallisation exotherm recorded. The half time was taken to be the minimum of the crystallisation peak.

TABLE 1

Polyester		A	B	C
Blocks		Random	Short	Long
Property (fresh)				
5	Mol percent HV	12	12	12
	MW moulding '000	435	299	338
	Tm °C	156.8	169.8	172.7
	ΔH_m J/g	60.6	45.2	54.7
	Tc °C	do not crystallise on cooling		
10	Cryst $t_{0.5}$, min at 70°C	5.83	4.25	2.5
	Cryst $t_{0.5}$, min at 120°C	6.27	5.73	2.07
	Tg °C	-0.1	-1.6	-0.5
Property (1 month after moulding)				
	Young's modulus MPa	1027	675	1049
15	Stress at peak load MPa	29	22.4	29.4
	Elongation to break %	11	10.7	11.1
	1mm notched IZOD impact J/m	85	113	79

It is evident that:

Melting points of B and C are substantially higher than
 20 for C and indeed approach that of PHB homopolyester
 (179°C);

Heat of melting is substantially less and may indicate
 less total crystallinity, especially for B;

Crystallisation is faster, especially for C; At 1 month
 25 after moulding, B is noticeably more flexible than the
 control;

At 1 month the impact strength of B is substantially
 greater than would be expected in view of its lower
 molecular weight than A.

30 Example 2

The procedure of runs B and C of Example 1 was

repeated with the modifications that the substrate ratio was adjusted to produce 7 or 8 mol percent HV units and the feed times in the long period runs were 12h instead of 13h. The products of these runs (D,E) were moulded as described above and tested one month after moulding in comparison with a random copolymer (F) and a blend (G) of PHB homopolymer with an 85:15 B:V copolymer to give a mean V content of 8 mol percent. Results are shown in Table 2.

10 **TABLE 2**

Polyester	D	E	F	G
Blocks	Short	Long	Random	Blend
Mol percent HV	7	8	8	8
MW moulding '000	554	371	418	429
15 Tm °C	155.5	159.2	148.8	172.9
t _{0.5} , min at 120°C	5.7	3.3	10.0	1.6
Young's modulus MPa	1160	1137	1241	1139
Stress at peak load MPa	31.46	30.18	32.27	30.61
Elongation to break %	14.74	9.37	7.32	8.37
20 1mm notched IZOD impact J/m	86.25	96.25	55.75	62.25

A useful increase in IZOD impact strength was achieved, with clear improvement in elongation to break, as compared with random or blended polyester.

Note: the microorganisms referred to herein by NCIMB numbers have been deposited with the National Collections of Industrial and Marine Bacteria Limited (NCIMB), PO Box 31, 135 Abbey Road, Aberdeen AB9 8DG, United Kingdom under the terms and conditions of the Budapest Treaty.

CLAIMS

1 A hydroxycarboxylic acid copolyester of R-stereospecific configuration which contains a majority of first repeating units capable of forming a highly crystalline high-melting homopolyester and a minority of second repeating units capable when randomly copolycondensed with said first repeating units of lowering the melting point of said homopolyester:

characterised by one or more of the following features:

- a a crystalline melting point higher by at least 10, especially by at least 15, °C than that of the corresponding random copolyester;
- b a half-crystallising time at 70°C or 120°C less than 0.9, especially less than 0.5, of that of the corresponding random copolyester;
- c IZOD 1mm notched impact strength at age 1 month at least equal to that of the corresponding random polyester of 20% higher molecular weight;
- d said majority repeating units in the polyester chain present in blocks longer than correspond to their over-all molar proportionality.

2 A copolyester according to Claim 1 in which the repeating units in the copolyesters include the residues of 3-hydroxybutyric acid (HB) and other hydroxy acids especially 4-hydroxybutyric acid (4HB) or 3-hydroxyvaleric acid (HV).

3 A copolyester according to Claim 2 in which HB units are at least 70 mol percent of the total units.

4 A process for making a copolyester according to any one of the preceding claims by fermentation, characterised by controlling the distribution of

repeating units by reference to the pattern of feeding substrates corresponding to the respective repeating units.

5 A process according to Claim 4 operated on a fed batch basis with alternating introduction of substrates corresponding to the respective repeating units, a predetermined fraction of the intended consumption of each substrate being fed over a period of time and then withheld until its concentration has fallen to a level between 1% of its maximum fed concentration and the level at which the organisms has begun to net-consume its store of polyester.

6 A process according to Claim 4 or Claim 5 including a polyester lay-down stage in which a nutrient essential for cell growth is limited, characterised in that the limiting nutrient is phosphorus but is fed at a concentration permitting a moderate extent of cell growth accompanying said polyester lay-down.

7 A process according to any one of Claims 4 to 6 in which the fermentation organism lacks metabolic pathways to produce HB units from substrates of odd carbon numbers.

8 A process according to any one of Claims 4 to 7 in which fermentation organism is Alcaligenes eutrophus.

9 A process according to any one of the preceding claims including recovery of copolyester from fermentation biomass by decomposition of non-copolyester cell material.

10 A process according to Claim 9 in which the copolyester is recovered as dry solid particles.

11 A process of making shaped articles by melt-shaping

a polyester according to any one of Claims 1 to 3 or made by a process according to any one of Claims 4 to 10.

12 A process according to Claim 11 in which the article is formed in its final shape without mechanical treatment to increase its crystallinity substantially.

13 A process according to Claim 9 in which the copolyester is recovered as a latex.

14 A process of making coated and/or bonded products by application of a latex of a copolyester according to any one of Claims 1 to 3 or as made by a process according to any one of Claims 4 to 9 and 13.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 95/02257A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C12P7/62 C08G63/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C12P C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 431 883 (IMPERIAL CHEMICAL INDUSTRIES PCL) 12 June 1991 see page 3, line 13 - page 4, line 30; claims 1-10	1-14
A	EP,A,0 052 459 (IMPERIAL CHEMICAL INDUSTRIES PCL) 26 May 1982 see claims 1-16	1-14

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

8 January 1996

Date of mailing of the international search report

29. 01. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Decocker, L

INTERNATIONAL SEARCH REPORT

Information on patent family members

national Application No

PCT/GB 95/02257

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-431883	12-06-91	AU-B- 637657	03-06-93
		AU-B- 6782790	13-06-91
		JP-A- 5236973	17-09-93

EP-A-52459	26-05-82	EP-A, B 0052460	26-05-82
		JP-C- 1782389	13-08-93
		JP-B- 4069186	05-11-92
		JP-A- 57111349	10-07-82
		JP-B- 6015604	02-03-94
		JP-A- 57150393	17-09-82
		JP-C- 1782493	13-08-93
		JP-A- 3149255	25-06-91
		JP-B- 4070342	10-11-92
		JP-A- 5015383	26-01-93
		US-A- 4393167	12-07-83
		AU-B- 560653	16-04-87
		AU-B- 8410882	13-01-83
		EP-A, B 0069497	12-01-83
		JP-B- 4038763	25-06-92
		JP-A- 58069224	25-04-83
		JP-A- 6172501	21-06-94
		JP-B- 7047623	24-05-95
		SU-A- 1375143	15-02-88
		US-A- 4477654	16-10-84
